

615

HTG #2 460

APPLICATION AREAS

- Bearings
- Conveyors
- Grinding Mills
- Blowers
- Crushers
- Mechanical Presses
- Cranes/Guides/Slides



PRODUCT DATA SHEET

KEY FEATURES AND BENEFITS

- Superior resistance to water washout
- Exceptional shear resistance
- Compatible with most greases
- NSF H2 - Registration number 133940
- Contains no toxic heavy metals
- Excellent for extremes in pressure and temperature
- ISO L-XCDIB2
- DIN 51 502-KPF 2P-30

PACKAGING

- 400g
- 18kg
- 180kg

DIRECTIONS

Apply with a grease gun, or brush on for local applications. Before using, wipe grease fittings to remove contamination. Keep grease container closed when not in use. Reapply at regular intervals.

DESCRIPTION

Chesterton® 615 HTG #2 460 is the one grease to use for the most demanding of lubrication needs. It is a multi-purpose workhorse with outstanding extreme pressure capabilities. With a temperature limit of 204°C, it performs at temperatures well beyond that of most conventional petroleum greases. The product is compatible with most other popular greases, has outstanding shear resistance and excellent corrosion resistance. Even when up to 50% water is incorporated into the product, the grease maintains its protective film and can withstand extremes of pressure. Uses for Chesterton 615 HTG #2 460 can be found throughout any industrial plant. It is especially advantageous where there is a high water environment such as in a pulp and paper mill, extremes of pressure such as in mining operations, or extremes of temperature such as in steel mills.

TYPICAL PHYSICAL PROPERTIES

Appearance	Tan
Consistency, NLGI	2
Texture	Buttery with slight tack
Specific Gravity	0.97
Dropping Point (ASTM D 566, DIN 51 801/1)	>300°C (572°F)
Penetration (ASTM D 217, DIN ISO 2137)	270
Timken OK Load (ASTM D 2509)	29.5 kg (65 lbs)
Four Ball Wear Test (ASTM D 2266, DIN 51 350/5)	
Scar diameter	0,4mm
Weld	500 kg (1102 lbs)
Load Wear Index	65
Operating Temperature (above 170°C, increased lubrication frequency is required)	-40°C (-40°F) to 204°C (400°F)
Shear Stability (ASTM D 217), % Change	
10,000 strokes	+1.4%
100,000 strokes	+2.8%
Oil Separation (ASTM D 1742), % loss	0.17%
Water Washout (ASTM D 1264) @ 79°C (175°F)	2.75%
Corrosion Resistance (ASTM B 117), 5% NaCl	>1000 hrs @ 50 micron film thickness
Base Oil Viscosity (ASTM 445, DIN 51 561)	
@ 40°C	500 cSt
@ 100°C	32 cSt

Before using this product, please refer to Safety Data Sheet (SDS).

