



MULTIFAK[®] EP

000, 00, 0, 1, 2

PRODUCT DESCRIPTION

Multifak[®] EP greases are multipurpose extreme pressure greases suitable for use in many industrial grease applications.

CUSTOMER BENEFITS

Multifak EP greases deliver value through:

- **Good water resistance** — Resistance to washout of bearings.
- **Good corrosion protection** — Inhibited to protect bearing surfaces.
- **Good oxidation stability** — Helps to support long life in storage and in use.
- **Simplified lubrication** — One grease designed to satisfy many different industrial grease requirements.
- **Low oil separation tendency** — Recommended for use in typical centralized lubrication systems.

FEATURES

Multifak EP greases are multipurpose extreme pressure greases suitable for use in many industrial grease applications.

Multifak EP greases are manufactured using selected highly refined medium viscosity index base oils, a lithium 12 hydroxystearate thickener, an extreme pressure additive, and rust and oxidation inhibitors.

NLGI grade 000 is red in color and stringy in texture. NLGI grades 00, 0, 1 and 2 are amber in color and buttery in texture.

Multifak EP greases have high load-carrying capacity and, therefore, provide good protection of lubricated parts against wear. They provide good lubrication in the presence of water, protect bearing surfaces against corrosion, and have excellent resistance to oxidation, which supports long life in storage and in use.

Product(s) manufactured in the USA and Colombia.

Always confirm that the product selected is consistent with the original equipment manufacturer's recommendation for the equipment operating conditions and customer's maintenance practices.

A **Chevron** company product

© 2008-2022 Chevron U.S.A. Inc. All rights reserved.

Chevron, the Chevron Hallmark and Multifak are trademarks owned by Chevron Intellectual Property LLC. All other trademarks are property of their respective owners.

Multifak EP greases are work stable. They resist separation or throw out from antifriction bearings. They have low oil bleeding tendency under pressure and are pumpable at low temperatures.

APPLICATIONS

Multifak EP greases are suitable for use in typical centralized lubrication systems.

Multifak EP greases can satisfy a wide range of industrial and commercial grease applications.

Typical applications include:

- General Machinery - plain, antifriction, roller, and needle bearings
- Construction equipment
- Conveyors and run-out rolls
- Crusher, shaker, or classifier screen bearings
- Chassis lubrication
- Non-disc brake wheel bearings

Multifak EP greases are recommended for both plain and antifriction bearings and particularly for bearings subjected to shock loading. **NLGI grades 1 and 2** comply with Timken's recommendation for this service.



NLGI grade 000 is a semifluid grease formulated to meet the lubrication requirements of machinery having enclosed gear cases where housings and seals have lost their ability to retain conventional gear oils.

NLGI grades 0, 00, 2 are approved by SMS Group SN 180-1.

NLGI grades 000, 00 and 2 are listed in the GROB Lubricant Chart.

NLGI grades 1 and 2 are NLGI LB certified.

1 May 2022
GR-67

NLGI grade 2 has Volvo 97718 approval.

NLGI grades 0, 1 and 2 are registered by **NSF** and are acceptable as a lubricant where there is no possibility of food contact (H2) in and around food

processing areas. The NSF Nonfood Compounds Registration Program is a continuation of the USDA product approval and listing program, which is based on meeting regulatory requirements of appropriate use, ingredient review and labeling verification.

TYPICAL TEST DATA

NLGI Grade	000	00	0	1	2
<i>Product Number</i>	274508	274509	274501	274502	274503
<i>SDS/MSDS Number</i>					
<i>USA</i>	38345	23689	23562	23562	23562
<i>Colombia</i>	—	—	—	—	34392
<i>Operating Temperature, °C(°F)</i>					
Minimum ^a	-35(-31)	-35(-31)	-30(-22)	-20(-4)	-15(5)
Maximum ^b	70(158)	77(170)	99(210)	125(257)	127(260)
<i>Penetration, at 25°C(77°F)</i>					
Unworked	445	415	390	305	275
Worked	460	415	370	325	280
<i>Dropping Point, °C(°F)</i>	160(320)	160(320)	171(340)	186(367)	188(370)
<i>Timken OK Load, lb</i>	40	40	40	40	40
<i>Thickener, %</i>	1.6	2.3	5.0	7.0	9.0
Type	Lithium	Lithium	Lithium	Lithium	Lithium
<i>ISO Viscosity Grade, Base Oil Equivalent</i>	320	100	220	220	220
<i>Viscosity, Kinematic*</i>					
cSt at 40°C	349	112	173	173	173
cSt at 100°C	22.3	9.8	15.6	15.6	15.6
<i>Viscosity, Saybolt*</i>					
SUS at 100°F	1880	595	914	914	914
SUS at 210°F	112	60	82	82	82
<i>Viscosity Index*</i>	76	49	90	90	90
<i>Flash Point, °C(°F)*</i>	224(435)	204(400)	204(400)	249(480)	249(480)
<i>Pour Point, °C(°F)*</i>	-27(-17)	-24(-11)	-12(-10)	-12(-10)	-12(-10)
<i>Texture</i>	Stringy	Buttery	Buttery	Buttery	Buttery
<i>Color</i>	Red	Amber	Amber	Amber to Brown	Amber to Brown

a Minimum operating temperature is the lowest temperature at which a grease, already in place, could be expected to provide lubrication. Most greases cannot be pumped at these minimum temperatures.

b Maximum operating temperature is the highest temperature at which the grease could be used with frequent (daily) relubrication.

* Determined on mineral oil extracted by vacuum filtration.

Minor variations in product typical test data are to be expected in normal manufacturing.

Always confirm that the product selected is consistent with the original equipment manufacturer's recommendation for the equipment operating conditions and customer's maintenance practices.