

ISO-9001 Registered Quality System. ISO-21469 Compliant.

Sales, Service & Distribution Center

Newark, NJ 07105

Phone: 973-589-9150 Fax: 973-589-4432

Manufacturing, Sales, Service & Distribution Center

Toledo, OH 43605

Phone: 419-691-2491 Fax: 419-693-3806

Sales and Tech Service Support

Phone: 1-800-733-4755

PRODUCT DATA

LUBRIPLATE "SFGO ULTRA" SERIES ISO VISCOSITY GRADES 100, 150, 220, 320, 460, 680 & 1000

"These products are certified OU Kosher Pareve"

*NSF International H-1 Registered NSF ISO21469 Certification

DESCRIPTION

LUBRIPLATE SFGO Ultra Series of synthetic hydrocarbon food grade fluids have been formulated with 100% pure PAO synthetic base oils. These Polyalphaolefin(PAO) based synthetic fluids are outstanding lubricants for use under severe conditions subject to extreme high and low temperatures. They exhibit outstanding oxidation resistance, thermal stability, anti-wear protection, and have the extreme pressure capabilities required for industrial gearboxes. These fluids are all zinc-free.

LUBRIPLATE strongly recommends the use of the LUBRIPLATE Oil Analysis Program to monitor performance, improve predictive maintenance and achieve the longest potential oil drain interval. SFGO Ultra Series has the potential to achieve 3 times or more the typical oil drain interval of mineral based oils. Contact your authorized LUBRIPLATE Distributor for more information on the LUBRIPLATE Oil Analysis Program.

APPLICATIONS

LUBRIPLATE SFGO Ultra Series is recommended for gearboxes, bearings, pumps, compressors, blowers, and chains requiring ISO Viscosity Grades 100 through 1000.

LUBRIPLATE SFGO Ultra Lubricants are compatible with most mineral base oils including LUBRIPLATE products such as LUBRIPLATE FMO-AW Series and LUBRIPLATE SPO Series. Always consult LUBRIPLATE before changing to an SFGO Ultra fluid from an existing lubricant that may not be compatible with Polyalphaolefin based fluids.

ADVANTAGES

- á Excellent thermal stability resulting in longer service life.
- Superior oxidation resistance.
- a Outstanding anti-wear properties providing extended equipment life.
- á Extreme pressure capabilities required for industrial gear boxes.
- á Exceptional demulsibility characteristics.
- á Superb corrosion inhibitor package.
- Maturally high viscosity index and low pour points which ensure optimum performance over a wide operating temperature range.
- á Superior cleanliness characteristics.
- Excellent compatibility with a variety of elastomers, seals, plastics
 and paints.











Typical Test Data – See Back

DACKACING AVAILABLE	1114 400	III440 450		
PACKAGING AVAILABLE	<u>Ultra 100</u>	<u> Ultra 150</u>		
Carton, 4/1 Gallon Plastic Jugs	L0983-057	L0984-057		
5 Gallon Pail	L0983-060	L0984-060		
16 Gallon Drum	L0983-061	L0984-061		
55 Gallon Drum	L0983-062	L0984-062		
PACKAGING AVAILABLE	Ultra 220	Ultra 320		
Carton, 4/1 Gallon Plastic Jugs	L0985-057	L0986-057		
5 Gallon Pail	L0985-060	L0986-060		
16 Gallon Drum	L0985-061	L0986-061		
55 Gallon Drum	L0985-062	L0986-062		
PACKAGING AVAILABLE	Ultra 460	Ultra 680		
FAURACINO AVAILABLE	Oitia 400	Oitra 000		
Carton, 4/1 Gallon Plastic Jugs	L0987-057	L0988-057		
Carton, 4/1 Gallon Plastic Jugs	L0987-057	L0988-057		
Carton, 4/1 Gallon Plastic Jugs 5 Gallon Pail	L0987-057 L0987-060	L0988-057 L0988-060		
Carton, 4/1 Gallon Plastic Jugs 5 Gallon Pail 16 Gallon Drum	L0987-057 L0987-060 L0987-061	L0988-057 L0988-060 L0988-061		
Carton, 4/1 Gallon Plastic Jugs 5 Gallon Pail 16 Gallon Drum 55 Gallon Drum	L0987-057 L0987-060 L0987-061 L0987-062	L0988-057 L0988-060 L0988-061		
Carton, 4/1 Gallon Plastic Jugs 5 Gallon Pail 16 Gallon Drum 55 Gallon Drum PACKAGING AVAILABLE	L0987-057 L0987-060 L0987-061 L0987-062 Ultra 1000	L0988-057 L0988-060 L0988-061		
Carton, 4/1 Gallon Plastic Jugs 5 Gallon Pail 16 Gallon Drum 55 Gallon Drum PACKAGING AVAILABLE Carton, 4/1 Gallon Plastic Jugs	L0987-057 L0987-060 L0987-061 L0987-062 Ultra 1000 L0989-057	L0988-057 L0988-060 L0988-061		

*NSF International H-1 Registration No.'s (Meets former USDA 1998 Guidelines)

 (Ultra 100)
 125682
 (Ultra 150)
 125683
 (Ultra 220)
 125539

 (Ultra 320)
 125540
 (Ultra 460)
 125541
 (Ultra 680)
 125542

(Ultra 1000) 125543

*Registered H-1 by NSF International for use in food processing facilities as a lubricant or anti-rust agent on equipment in which there may be incidental contact involving the lubricated part and the edible product.

"The LUBRIPLATE SFGO Ultra Series contains no components derived from TSE/BSE relevant animal species; therefore, it is compliant with the requirements of the TSE Note for Guidance EMA/410/01 Rev. 3 July 2011".

Manufactured with ingredients that comply with FDA 21 CFR 178.3570 and FDA 21 CFR 172.882.

STORAGE RECOMMENDATIONS

- á Products should be stored between 40°F-120°F
- á Products should be stored in a dry covered environment
- á Products should not be stored in warm, direct sunlight
- á Improper storage conditions can significantly alter the shelf life of the product. Such conditions would include temperature, moisture, open containers, etc.

[&]quot;These products are Halal certified"

PROPERTY	TEST METHOD	TYPICAL RESULTS*						
		SFGO Ultra 100	SFGO Ultra 150	SFGO Ultra 220	SFGO Ultra 320	SFGO Ultra 460	SFGO Ultra 680	SFGO Ultra 1000
Viscosity SUS @ 100°F	ASTM D-2161	556	762	1088	1557	2143	3289	4900
Viscosity SUS @ 210°F	ASTM D-2161	77	97	128	161	211	275	372
Viscosity cSt @ 40°C	ASTM D-445	98	146	222	318	452	623	950
Viscosity cSt @ 100°C	ASTM D-445	14	19	26	34	46	57	77
Viscosity Index	ASTM D-2270	145	141	146	152	159	157	157
Pour Point	ASTM D-97	-43°F/-42°C	-43°F/-42°C	-42°F/-41°C	-40°F/-40°C	-40°F/-40°C	-45°F/-43°C	-35°F/-37°C
Flash Point	ASTM D-92	485°F/252°C	495°F/257°C	520°F/271°C	520°F/271°C	480°F/249°C	500°F/260°C	500°F/260°C
Fire Point	ASTM D-92	520°F/271°C	525°F/274°C	540°F/282°C	545°F/285°C	515°F/268°C	545°F/285°C	545°F/285°C
API Gravity	ASTM D-287	33.9	33.2	32.6	32.0	31.1	34.5	33.7
Color	ASTM D-1500	1.0 max						
4-Ball Wear Test	ASTM D-2266	0.32 mm	0.32 mm	0.32 mm	0.31 mm	0.31 mm	0.31 mm	0.30 mm
FZG Scuffing, A/8.3/90 Failure Stage	ASTM D5182/ DIN 51354			>14	>14	>14		
Demulsibility Characteristics	ASTM D-2711							
Procedure B; Run 1: Percent of Water in Oil		0.3%	***	***	***	***	***	***
Free Water Volume		86.8 ml	***	***	***	***	***	***
Emulsion Volume		0.0 ml	***	***	***	***	***	***
Demulsibility Characteristics	ASTM D-2711							
Procedure B; Run 2: Percent of Water in Oil		0.4%	***	***	***	***	***	***
Free Water Volume		86.0 ml	***	***	***	***	***	***
Emulsion Volume		0.0 ml	***	***	***	***	***	***
Demulsibility Characteristics	ASTM D-2711							
Procedure B; Average: Percent of Water in Oil		0.4%	***	***	***	***	***	***
Free Water Volume		86.4 ml	***	***	***	***	***	***
Emulsion Volume		0.0 ml	***	***	***	***	***	***

Note: LUBRIPLATE SFGO Ultra 220, SFGO Ultra 320 & SFGO Ultra 460 passed ASTM D-5182 and DIN 51354 Modified to 13 and 14 Stages.

Slight variations in product color may occur due to storage temperature and exposure to light. Product color has no impact on the lubricant's performance or to the food safety rating of this NSF H1 and ISO21469 certified product.